



**PARSHVA
POLYMERS**

TEST CERTIFICATE

PRODUCT DESCRIPTION	TYPE
Product Code	PARSPOLYCAR - 2113
Colour	Black
Invoice No	
Date	

PROPERTIES	REFERENCE STD	UNIT	OBSERVED VALUE
Density	ASTM D 792	g/cc	1.24
Ash Content	ASTM D 5630	%	0
MFI @ 0.47Mpa	ASTM D-1238	Gm/10 Min	15.3
Heat Deflection Temp	ASTM D 648	°C	270
Tensile Strength	ASTM D 638	MPA	95
Flexural Strength	ASTM D 790	MPA	115
Flexural Modulus	ASTM D 790	MPA	3450
N.Izod Impact Strength	ASTM D 256	J/M	12
Moisture	ASTM D 570	%	0.09

For Parshva Polymers

Authorised Signatory

Note : Properties measured at DAM Condition

Signatory not required when transmitted electronically.



QC-09A/00

www.ParshvaPolymers.in

info@parshvapolymer.in